



ANH Refractories Europe Ltd

Dock Road South, Bromborough

Wirral, England, CH62 4SP

Tel +44 (0)151 641 5900

Fax +44 (0)151 641 5910

Email sales@anheurope.co.uk

Web www.anheurope.co.uk

For Mixing and Using KD2

KD2 contains a small percentage of combined sulphur and should not be used where sulphurous gases may affect kiln ware or electric elements

KD2 can be stored indefinitely providing it is not contaminated in storage with other materials and remains dry. Partially used bags can be returned to store and used later with no detriment to mixing, working and bonding properties. In its dry state KD2 is not affected by sub-zero temperatures.

KD2 should be mixed with clean potable water only. The water addition may be varied slightly to modify the consistency to suit the particular job but should be in the region of

12 to 15 Litres of water per 100 Kgs KD2 approx.

Dry out and heat up schedules will be governed by those of the brick work.

Store in Dry Place

